



Step #	Installation Step	Installation Methods	Products & Mix Ratios	Theoretical Coverage Rates
1	<p>Surface Preparation</p> <p>Concrete (Minimum CSP 3)</p> <p>Other Surfaces:</p>	<p>Shot blast or diamond grind</p> <p>White pad buff, solvent wipe</p>	N/A	N/A
2	<p>Apply 1st Coat of Drylook Sealer</p> <p>Caution: Avoid application of sealer when surfaces are hot from the sun. Attempt to schedule work during cooler hours and in more shady areas.</p>	<p>a. Dip and Roll or</p> <p>b. Airless Spray and Backroll or</p> <p>c. Hudson-type sprayer and Backroll</p> <p>d. Brush for detail work</p>	<p>Miracote Drylook Sealer</p> <p>Note: Wipe excess amounts up with soft, dry cotton cloth or absorbent paper towels.</p>	<p>800 SF/Gal 2 mils WFT</p> <p>Note: Coverage depends on surface texture and profile. Consumption may be greater on more irregular surfaces.</p>
3	<p>Apply 2nd Coat of Drylook Sealer</p> <p>Caution: Avoid application of sealer when surfaces are hot from the sun. Attempt to schedule work during cooler hours and in more shady areas.</p>	<p>a. Dip and Roll or</p> <p>b. Airless Spray and Backroll or</p> <p>c. Hudson-type sprayer and Backroll</p> <p>d. Brush for detail work</p>	<p>Miracote Drylook Sealer</p> <p>Note: Wipe excess amounts up with soft, dry cotton cloth or absorbent paper towels.</p>	<p>800 SF/Gal 2 mils WFT</p> <p>Note: Coverage depends on surface texture and profile. Consumption may be greater on more irregular surfaces.</p>

Note: Prior to starting the application of any Miracote Product or System be sure to read the Installation Guideline Manual. Appendices, Product Data Sheets, MSDS and other pertinent documents published by Crossfield Product Corp. for information, including but not limited to, Precautions, Limitations, Disclaimers and Warranties.

Pay special attention to substrate moisture content, physical condition of the substrate, method(s) of surface preparation, surface restoration, detailing of cracks, joints, transitions and terminations, and any applicable specifications. Review carefully for unknown site conditions or defects.

The theoretical coverage rates stated in the Installation Guides are for estimating purposes only. Factors, such as, allowance for material waste, unusual or abnormal substrate conditions and other unforeseen job site conditions that may affect actual product yields are the responsibility of the installer.