



Product Technical Data Sheet

MIRACOTE[®] MIRATHANE 500

1. PRODUCT DESCRIPTION

A. COMPOSITION

Mirathane 500 is a trowel-applied elastomeric surfacing designed primarily for use as a waterproof promenade roofing. The material consists of a unique moisture-cured resin binder into which rubber aggregate is combined at the time of application to form a tough, elastic waterproof membrane. A durable elastomeric textured topcoat is then applied. An alternate topcoat system incorporating decorative mineral aggregates is also available. The material is turned up against building walls, parapets, etc., to form an integral waterproof membrane.

Designed primarily as a waterproof promenade surfacing for balconies, sun decks, play roofs, etc., Mirathane 500 is also used as a protective covering for renovating cracked concrete decks, parking structures, etc. The tough, long-wearing qualities of Mirathane 500 permit its use under such normally damaging service as ski boot traffic.

Surfaces over which Mirathane 500 may be installed include: plywood, new and existing concrete and metal. Consult Crossfield Products Corp. regarding other surfaces.

B. TYPICAL USES

Promenade roofs, sun decks, rooftop tennis courts, and balconies; waterproof surfacing for areas subject to ski boots.

C. ADVANTAGES AND LIMITATIONS

ADVANTAGES:

1. Monolithic, including integral flashing.
2. Resilient and comfortable underfoot.
3. Reduces sound transmission to adjacent areas.
4. Environmentally safe – Meets various state volatile organic compound requirements.

LIMITATIONS:

1. Substrate must be dry when material is applied.

2. TYPICAL PHYSICAL PROPERTIES at 75°F (24°C)

A. Weight	0.46 lbs/sq. ft
B. Thickness (typical)	1/16" (62.5 mils)
C. Elongation ASTM D412	500%
D. Tensile Strength ASTM D412	1,050 psi
E. Waterproofness	No water transmission (Sample exposed to 50 psi water pressure for 1 hour)
F. Adhesion ASTM D903	175 psi
G. Hardness ASTM 2240	Shore "A" 60-70
H. Crack Bridging and Low Temperature Flexibility ASTM C836	Complies

3. INSTALLATION

- A. Prepare surface by careful and thorough removal of laitance, grease, and concrete curing agents and foreign matter. Consult Crossfield Products Corp. for acid etching or shot-blasting requirements.
- B. Apply epoxy primer by roller.
- C. Apply Mirathane 500 basecoat by trowel and broadcast with rubber granules.
- D. Apply pigmented topcoat.

4. PRODUCT AVAILABILITY

Crossfield Products Corp. maintains offices and/or factories at all addresses listed below. Factory Trained Contractors are established in all major trading areas in the United States, Canada and various European, Latin American and Far East nations.

5. SLIP RESISTANCE and CLEANABILITY

In general, the more aggressive the finished surface the greater the coefficient of friction and corresponding slip resistance, the more difficult to clean. The smoother the finished texture the easier the surface is to clean, but there is a loss of skid resistant properties.

6. CLEANING

Cleaning and disinfecting compounds and cleaning techniques can affect the color, gloss, texture and performance of the system. As a precautionary step, Crossfield recommends that the end-user test their cleaning and disinfecting compounds on a sample or on a small, out of the way finished area, utilizing the intended cleaning technique prior to cleaning the entire surface area. If no deleterious effects are observed, the procedure can be continued. If the cleaning and disinfecting compounds or cleaning techniques damage the system, modification of the cleaning material or techniques will be required. Contact your Representative for additional information.

7. MAINTENANCE

For maximum sheen and cleanability, floor should be routinely treated with conventional maintenance finish followed by ordinary buffing.

8. SPECIFICATION ASSISTANCE

Consult Crossfield Products Corp. for specification assistance, detailing, etc. This consultation is highly recommended prior to specification.

9. CHEMICAL RESISTANCE

See Crossfield Products Corp's. Chemical Resistance Guidelines for chemical resistance of a product or system, as well as the types of test performed:

- ASTM C868 Standard Test Method for Chemical Resistance of Protective Lining.
- ASTM C267 Standard Test Method for Chemical Resistance of Mortars, Grouts, and Monolithic Surfacing and Polymer Concretes.
- ASTM D1308 Standard Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes.
- Crossfield Products Corp. Proprietary Testing.

Note: Chemical resistance is a functional test, usually limited to changes in weight or thickness measured in loss or gain and does not evaluate subject aesthetic issues. To determine aesthetic issues, Crossfield recommends testing the products or system in accordance with intended end use.

10. TESTING

The technical data contained herein is the result of tests made in Crossfield's laboratories or in independent laboratories using small scale equipment, following generally accepted trade practices. Although this information is believed to be true and accurate, the use of different equipment for testing under dissimilar conditions or the testing of samples produced under dissimilar conditions may develop substantially different results.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICES ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield's examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIAL NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



MIRACOTE PRODUCT LINE Crossfield Products Corp.

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA
90221
310-886-9100
310-886-9119 fax

East Coast Office
140 Valley Road
Roselle Park, NJ
07204
908-245-2800
908-245-0659 fax

www.miracote.com