



Epoxy &  
Polyurethane  
Manufacturing and  
Research

## TECHNICAL BULLETIN

### Coefficient of Friction Table

| Product                    | Neoprene* | Leather* |
|----------------------------|-----------|----------|
| SS 1120                    | 1.16      | 0.93     |
| SS 1202                    | 0.806     | 0.675    |
| SS 1540                    | 0.856     | 0.825    |
| SS 1600                    | 0.95      | 0.625    |
| SS 2700                    | 0.95      | 0.744    |
| SS 3300                    | 0.719     | 0.544    |
| SS 3700                    | 0.819     | 0.631    |
| SS 3700 CF                 | 0.863     | 0.778    |
| SS 3800                    | 0.900     | 0.705    |
| Stone Tone Wax             | 1.025     | 0.850    |
| Rembrandt<br>Polymer Stain | 1.00      | 0.969    |

\*Test Method MIL-PRF 24613 (Paragraph 4.8.6) – Typical Results

#### Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss, or damage resulting from use of this product.

**Service is part of our formula**

#### Epmar Corporation

13210 Barton Circle, Santa Fe Springs, CA 90605-3254

Ph: 562.946.8781 / Fax: 562.944.9958

E-Mail: [epmar@quakerchem.com](mailto:epmar@quakerchem.com) Web Site: [www.epmar.com](http://www.epmar.com)