

D-GUARD WB 309

Non-Yellowing, Penetrating, Water Based Cure & Seal Compound

Product Description

D-Guard WB 309 is a non-yellowing, water based product designed for curing and sealing applications. D-Guard WB 309 is a penetrating and breathable coating that provides a satin or low gloss finish to a multitude of interior & exterior horizontal or vertical concrete and masonry finishes. D-Guard WB 309 is self-cross linking, which provides better film formation, early water resistance, adhesion, toughness and outstanding efflorescence and alkali resistance. It can be applied to green concrete. D-Guard WB 309 provides enhanced performance over traditional acrylics with better flexibility, chemical resistance, non-blushing, adhesion, durability and hot tire resistance.

Benefits & Features

- Perfect for low ventilated areas where low VOC's and no fumes are required
- Non-yellowing formula assures product's superior resistance to the elements
- Deep penetrating and ultra low viscosity formula allows for easy application through sprayers
- Superior efflorescence and alkali resistance compared to common solvent based acrylic sealers.

Recommended Applications

D-Guard WB 309 is recommended for interior & exterior freshly placed, finished, and aged concrete where a penetrating, low-gloss water based curing and sealing compound is specified.

Technical Information

Solids	15%	Wet Appearance	Milky White
Drying Time	1-2 Hours	Dry Appearance	Clear and Satin Gloss
Re-Coat Time	4-24 Hours	VOC Content	<300 g/l
Foot Traffic	4-6 Hours	Blush Resistance	Good
Wheel Traffic	24-48 Hours	Solvent Resistance	Superior
Application Temp	50°F - 85°F	Concrete Adhesion	Excellent

***Please note that low air and/or concrete temperatures and/or relative humidity may extend drying times. Follow recommended coverage rates for best results.

Specifications/Compliances

Classified in Table 1.1 ACI Standard 302 ASTM C 309, Type 1, Class A&B Corps of Engineers CRD-C304, Type 1 Class A&B
AASHTO M-148 USDA Compliant for use in meat and poultry areas

Approximate Coverage Rates

New (unsealed) concrete 200-250 ft² Old (sealed) Concrete 350-400 ft²

*Coverage rates vary depending upon surface porosity and texture, and application method. Excessive build up should be avoided.

Shelf Life

D-Guard WB 309 has a shelf life of up to one year in it's original, sealed, unopened container.

Packaging

D-Guard WB 309 is packaged in 1 gallon cans, 5 gallon pails, and 55 gallon drums.

ORRVILLE
133 North Kohler Road
Orrville, Ohio 44667
(330) 682-5678

CLEVELAND
7941 Granger Road
Cleveland, Ohio 44125
(216) 573-0770

COLUMBUS
690 Harrison Drive
Columbus, Ohio 43204
(614) 253-3326



www.eco-cretesupply.com

Instructions for Use

Surface Preparation: Concrete surface must be clean and free of all contaminants and water. Do not apply if rain is forecast within 24 hours. If moisture is present or if the surface is not clean and free of all containments, the sealer may have white spots and have premature delamination and failure. May be applied when damp (not “wet”) to freshly placed concrete surfaces.

Substrate temperature must be no less than 40 degrees F and not exceed 80 degrees F. If applied outside these limits the sealer may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing.

Mixing: Stir well before using. Material may separate during long term storage.

Application: Apply using a 3/8” long nap roller cover using long even uniform strokes at approximately 250-400 square feet per gallon depending on porosity and texture of substrate. An airless sprayer containing a .519 tip size may be used as well. Thick or puddle areas may prevent the solvent from evaporating and may be susceptible to moisture intrusion which may cause milky white spots. Applying too thin may cause sealer to prematurely delaminate, flake, or wear away. Allow sealer to dry for 24 hours for light traffic and at least 48 hours for heavy traffic. If applying two coats, wait approximately 4-6 hours between coats.

Please Note: It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture, etc. If applying by spray method, extended coverage rates may be achieved, but be aware that less material will be applied and inadequate film formation or performance expectations may be limited.

Clean-Up

Use soap and warm water. Dispose of containers in accordance with local and federal regulations.

Product Removal

Dried, cured sealer may be removed using a diamond grinding method, sandblasting method or similar mechanical action. Other forms of removal may be acceptable.

Precautions & Limitations

- This product will freeze during storage. Do not store in areas where temperatures will drop below 32 degrees F.
- It is recommended to store this product in an area where the temperature is between 50 and 80 degrees F
- Do not allow D-Guard WB 309 to be subject to any form of rain or moisture for 18-24 hours after application.
- It is not recommended to apply D-Guard WB 309 over carpet, tile, and other types of floor adhesives.
- Coverage rates depend upon many conditions including application method, surface porosity, applicator, etc.
- D-Guard WB 309 was designed for curing and sealing applications and to be applied in one-two thin coats, not one thick coat.
- Please be aware that this product when cured may be slippery when wet
- D-Guard WB 309 should never be thinned or mixed with any form of liquid or solvent.
- It is not recommended to thin D-Guard WB 309. Improper thinning may cause sealer to delaminate in a short time frame.
- D-Guard WB 309 may slightly darken the surface of many new and existing concrete slabs. Test prior to use.

Special Notes

Please consult Safety Data Sheet (SDS) and read warranty information prior to use. This information can be requested by contacting customer service at 330-682-5678.

ORRVILLE

133 North Kohler Road
Orrville, Ohio 44667
(330) 682-5678

CLEVELAND

7941 Granger Road
Cleveland, Ohio 44125
(216) 573-0770

COLUMBUS

690 Harrison Drive
Columbus, Ohio 43204
(614) 253-3326

