



Description

Kemiko Stone Tone Sealer II is a single component, acrylic waterbased sealer that offers low VOC, is very user friendly and is designed for sealing concrete to provide resistance against water, alkali, acids, UV light, and staining. Kemiko Stone Tone Sealer II is supplied in clear gloss and satin finish, and is a non-yellowing interior and exterior concrete coating.

Applications

Kemiko Stone Tone Sealer II is applied to properly prepared concrete, and utilized as a resilient protective finish coat over Kemiko Stone Tone Stains and Rembrandt Polymer Stains. Typical applications include commercial and residential cement floors, hospitals, showroom floors, schools, shopping malls, and many other interior floor surfaces requiring additional protection. Excellent replacement product for high VOC lacquers, acrylics, and varnishes, which cures fast to a hard resilient film with excellent flow properties.

Performance

VOC	<100 g/l
Pencil Hardness	2H-3H ASTM D-3363
Dry Tape Adhesion	5A-5B ASTM D-3359
Stain Resistance	Catsup, Soft Drinks, Wine, House Dressing, and Commercial Cleaners
Excellent Leveling & Flow	Brush, Roll & Spray Applications
Coefficient of Friction (ASTM F609)	
- Gloss	0.70
- Flat	0.70

Physical Characteristics

Volume Solids	21%
Packaging	1 gal & 5 gal (premeasured kits)
Gloss	High Gloss >90 @ 60° / Satin 40-50 @ 60°
Dry Time	@ 70°F 50% RH 30 minutes to touch 1 hour to recoat – foot traffic 4 hours Heavy traffic in 24 hours Full cure in 48 hours (washability)
Film Thickness	3-4 mils wet to achieve –1.0-1.5 mils dry DO NOT EXCEED RECOMMENDED FILM THICKNESS – AIR ENTRAPMENT OR FOAMING MAY OCCUR
Coverage	300-400 ft ² /gallon – per coat
Thinning	None required



Concrete Coatings & Floor Systems

TECHNICAL BULLETIN Kemiko® Stone Tone Sealer II

Surface Preparation

Bare Concrete —

All visible oil, grease, sludge, and any other contaminants shall be removed prior to any abrasive surface preparation, acid etching and water washing. Surface shall be cured, dry and free from alkali stain and laitance. Blas-Trac is preferred for long term adhesion and non-slip surface.

Existing Coatings —

Wash off any chalk, remove all visible grease, oil, dirt, or any other deleterious matter. Spot prime surfaces prior to full application coat. Warning! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop.

Clean Up — Use mild soap and tap water for cleanup.

Application Methods

Brush —

Use top quality bristle brush for best film properties.

Roller —

Lambswool or similar cover with phenolic core, ¼ inch nap thickness.

Spray —

Commercial conventional air spray or airless spray equipment utilizing spray gun tip size between .013"-.015". Adjust pressure for proper atomization.

Environment —

Apply between 50°F – 100°F and 5°F above dew point.

Safety —

Surfaces subjected to water may become slippery if coated with Kemiko Stone Tone Sealer II. If you must seal these surfaces, keep the sealer film build-up to a minimum. In severe cases, a nonslip material such as fine glass beads, washed silica sand and other aggregates may be broadcast between coating applications.

Note: the coating is not recommended for hot tire pick up.

Contact EPMAR for any additional application information.

Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss, or damage resulting from use of this product.



Epmar Corporation
13240 Barton Circle, Santa Fe Springs, CA 90605-3254
Ph: 562.946.8781 / Fax: 562.944.9958
www.epmar.com / www.kemiko.com