




Step #	Installation Step	Installation Methods	Products & Mix Ratios	Theoretical Coverage Rates
1	<p>Mechanically Prepare and Presaturate the Concrete Substrate</p> <p>Note: Minimum (CSP) concrete surface profile of CSP-3 or higher is required depending on substrate conditions & coating requirements.</p>	<p>a. Sandblasting or b. Shotblasting or c. Diamond grinding or d. Other similar and approved mechanical methods. e. Saturate with potable water</p>	<p>Miracote MPC (Multipurpose Protective Coating) must be applied to a clean, sound, and mechanically prepared concrete substrate, as per ICRI's Technical Guide No.03732, "Selecting and Specifying Concrete Surface Preparation". Concrete substrate should be (SSD) Saturated Surface Dry with no standing water at the time of application.</p>	N/A
NOTE:	<p>Climatic conditions that are associated with high rates of evaporation can decrease Miracote MPC working time. Add 1 unit of Miracote Retarder to increase valuable working time when these conditions are present or anticipated.</p>			
2	<p>Apply 1st Miracote MPC Coat</p> <p>Note 1: ColorPax-LIP (Liquid Integral Pigment) packs must be dispensed and mixed into the 5 Gal pail of Miracote MPC Liquid Catalyst. Note 2: ColorPax-LIP pigmented MPC colors are based on use with White powder. The use of Gray powder will produce a different color.</p>	<p>a. Hand Trowel or b. Magic trowel or c. Squeegee or d. Hopper Gun or e. Similar spray method (Low Pressure 8 -15 psi)</p> <p>Note: Recommended nozzle size of 8mm or 1/4"</p>	<p>Blend: Miracote MPC Liquid Catalyst and Miracote MPC Powder Mix Ratio: 5 Gal Miracote MPC Liquid Catalyst to (2) 55 LB Bags Note: Climatic conditions that are associated with high rates of evaporation can decrease Miracote MPC working time. Add 1 unit of Miracote Retarder to increase valuable working time when these conditions are present or anticipated.</p> <p>Mix Option 1 (Not Pigmented) Mix Gray or White Regular MPC</p> <p>Mix Option 2 (Pigmented) Mix Gray or White Regular MPC with (1) ColorPax-LIP Unit</p>	<p>500 SF/Unit</p> <p>Note: Coverage can vary depending on surface profile & condition.</p>
3	Place Tape and/or Stencil Faux Pattern	When 1st Miracote MPC Application Coat is cured, lay out pattern using Pre-cut Adhesive Backed Plastic Stencil or Filament Tape		
4	<p>Optional - Apply 2nd Miracote MPC Coat</p> <p>Note 1: Use same color as the 1st Miracote MPC coat to lock in stencil or tape to prevent bleed into simulated grout lines. Note 2: This step is at contractor's option, but is highly recommended per note 1.</p>	<p>a. Hand Trowel or b. Magic trowel or c. Squeegee or d. Hopper Gun or e. Similar spray method (Low Pressure 8 -15 psi)</p>	<p>Blend: Miracote MPC Liquid Catalyst and Miracote MPC Powder Mix Ratio: 5 Gal Miracote MPC Liquid Catalyst to (2) 55 LB Bags Mix Option 1 (Not Pigmented) Mix Gray or White Regular MPC Mix Option 2 (Pigmented) Mix Gray or White Regular MPC with (1) ColorPax-LIP Unit</p>	500 SF/Unit
5	<p>Apply 3rd Miracote MPC Coat</p> <p>Faux Finish Texture</p>	<p>a. Hand-trowel or b. Skip-trowel or c. Hopper-gun & knockdown d. Other methods, as desired</p>	<p>Blend: Miracote MPC Liquid Catalyst and Miracote MPC Powder Mix Ratio: 5 Gal Miracote MPC Liquid Catalyst to (2) 55 LB Bags Mix Option 1 (Not Pigmented) Mix Gray or White Regular MPC Mix Option 2 (Pigmented) Mix Gray or White Regular MPC with (1) ColorPax-LIP Unit</p>	500 SF/Unit

Step #	Installation Step	Installation Methods	Products & Mix Ratios	Theoretical Coverage Rates
1	 For antiquing options with acid or water based stains/dyes, please review the IG's for Miracote Mirastain.			Nominal 3/32 Inch

Choose any of the Miracote sealers or topcoats for best results depending on location, service, use and exposure. Refer to the Product Technical Data Sheets and Installation Guides for MiraGard Colorbond, MiraGard HDWB, MiraGard HD 400, MiraGard HD 100 MiraFlor WB or MiraThane WB.

Note: Prior to starting the application of any Miracote Product or System be sure to read the Installation Guide(s), Product Data Sheets, MSDS and other pertinent documents published by Crossfield Product Corp. for information, including but not limited to, Precautions, Limitations, Disclaimers and Warranties.



Pay special attention to substrate moisture content, physical condition of the substrate, method(s) of surface preparation, surface restoration, detailing of cracks, joints, transitions and terminations, and any applicable specifications. Review carefully for unknown site conditions or defects.

The theoretical coverage rates stated in the Installation Guides are for estimating purposes only. Factors, such as, allowance for material waste, unusual or abnormal substrate conditions and other unforeseen job site conditions that may affect actual product yields are the responsibility of the installer.



