

Physical Properties Bulletin

PlatSil® 71-Series, PlatSil® 73-Series, PlatSil® Gel Series, PlatSil® FS-Series Silicone Rubber Products

Product	Mix Ratio	Part A Color	Part B Color	Pour Time (min)	Demold Time	Total Cure Time (hr)	Specific Gravity	Mix Viscosity (cP)	Shore Hardness	Tensile Strength psi (MPa)	% Elongation	Linear Shrinkage	Die B Tear Strength pli (kN/m)	Die T Tear Strength pli (kN/m)
PlatSil 71-Series														
PlatSil® 71-10	1A:10B	Clear	Pink ¹	5	30 min.	24	1.06	3,500	A10	173 (1.19)	311	Nil	42 (7.35)	ND
PlatSil® 71-11	1A:1B	Blue ¹	Green ¹	20	4 hr.	24	1.12	6,000	A10	281 (1.93)	751	Nil	117 (20.48)	36 (6.31)
PlatSil® 71-20	1A:1B	Blue ¹	Pink ¹	25	4 hr.	24	1.12	12,000	A20	368 (2.54)	530	Nil	117 (20.48)	33 (5.78)
PlatSil® 71-30	1A:10B	Green ¹	White	60	24 hr.	48	1.12	25,000	A30	561 (3.87)	419	Nil	140 (24.51)	ND
PlatSil® 71-35	1A:10B	Blue ¹	White	60	24 hr.	48	1.12	25,000	A35	635 (4.38)	413	Nil	145 (25.39)	37 (6.48)
PlatSil® 71-40 1A:5B	1A:5B	Clear	White	60	24 hr.	48	1.10	25,000	A40	366 (2.52)	386	Nil	60 (10.51)	17.1 (3.00)
PlatSil® 71-40 1A:10B	1A:10B	Clear	Clear	90	24 hr.	48	1.04	38,000	A40	438 (3.02)	296	Nil	98.6 (17.26)	32.9 (5.76)
PlatSil 73-Series														
PlatSil® 73-15	1A:1B	White	White	20	4 to 5 hr.	48	1.10	2,500	A15	265 (1.82)	640	Nil	55 (9.63)	17 (2.98)
PlatSil® 73-20	1A:1B	Blue	Blue	5	5 hr.	24	1.10	3000	A22	230 (1.58)	460	Nil	45 (7.87)	17 (2.98)
PlatSil® 73-25	1A:1B	Yellow	Green	15	4 to 5 hr.	48	1.14	6,000	A25	380 (2.61)	405	Nil	120 (21.02)	30 (5.25)
PlatSil® 73-29	1A:10B	Clear	White	45	16 hr.	48	1.10	15,000	A30	542 (3.74)	531	Nil	90 (15.76)	39 (6.83)
PlatSil® 73-40	1A:10B	Yellow	White	45	16 hr.	48	1.10	15,000	A40	465 (3.21)	355	Nil	52 (9.11)	7 (1.23)
PlatSil® 73-45	1A:10B	Green ¹	Tan	40	16 hr.	48	1.27	35,000	A45	631 (4.35)	707	Nil	145 (25.39)	62.9 (11.01)
PlatSil® 73-60	1A:10B	Blue ¹	Tan	45	16 hr.	48	1.29	40,000	A60	537 (3.70)	202	Nil	113 (19.79)	45 (7.88)
PlatSil® SiliGlass	1A:1B	Clear	Clear	7	30 min.	24	0.97	200	A40	NA	NA	NA	NA	NA
PlatSil® SiliFoam	1A:1B	Clear	Milky White	45 sec	30 min.	24	15 lb/ft ³	7,500	NA	NA	NA	NA	NA	NA
PlatSil Gel Series														
PlatSil® Gel-OO20	1A:1B	Milky White	Milky White	40	2 hr.	24	1.05	3,900	OO20	122 (0.84)	964	Nil	24.8 (4.34)	1.3 (0.52)
PlatSil® Gel-OO30	1A:1B	Milky White	Milky White	45	4 hr.	24	1.05	6,200	OO30	118 (0.81)	848	Nil	36.6 (6.41)	10.7 (1.87)
PlatSil® Gel-OO	1A:1B	Milky White	Milky White	6	30 min.	24	1.10	22,000	OO30	154 (1.06)	1275	Nil	56 (9.81)	19 (3.33)
PlatSil® Gel-10	1A:1B	Milky White	Milky White	6	30 min.	24	1.10	15,000	A10	228 (1.57)	970	Nil	80 (14.01)	27 (4.73)
PlatSil® Gel-25	1A:1B	Milky White	Milky White	5	1 hr.	24	1.12	3,500	A25	434 (2.99)	385	Nil	146 (25.56)	28 (4.90)
PlatSil FS-Series														
PlatSil® FS-10	1A:1B	Milky White	Milky White	8	25 min.	24	1.11	4,200	A13	488 (3.36)	679	Nil	157.9 (27.6)	54.8 (9.59)
PlatSil® FS-20	1A:1B	Milky White	Milky White	8	25 min.	24	1.11	3,800	A20	467 (3.22)	626	Nil	148.2 (25.9)	52.8 (9.24)

¹ Component requires stirring before use.

Conventions: psi/145 = MPa (megaPascals)

pli x .1751 = kN/m (kiloNewtons per meter)

ND = Not Determined

Disclaimer: The information in this bulletin and otherwise provided by Polytek is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained by the use thereof, or that any such use will not infringe any patent. The user shall determine the suitability of the product for the intended use and assumes all risk and liability whatsoever in connection therewith.