



## Concrete Coatings & Floor systems

## TECHNICAL BULLETIN Kemiko® Easy Shine Acrylic Mop On Wax (48 series)

### Description

Kemiko® Easy Shine (48 series) is a single component waterborne acrylic polymer wax for protecting and maintaining sealed concrete and many other finished substrates. Kemiko® Easy Shine is designed to be a maintenance coating with properties that include the ability to repel water, reduce scuffing, and minimize marring. Kemiko® Easy Shine allows the substrate to breathe, is low odor, low-VOC, extremely user-friendly, and comes in a high gloss or satin finish.

### Applications

Kemiko® Easy Shine™ (48 series) can be applied to properly prepared Kemiko® or Rembrandt™ stained floors sealed with Kemiko® Stone Tone™ Sealer II, Kemiko® 100% Solids and Water Base Epoxies, Kemiko® Water Base Polyurethane, and Kemiko® Aliphatic Polyaspartic. Easy Shine™ is also compatible with many other sealed concrete products. Typical applications include commercial kitchens, grocery stores, restaurants, showroom floors, walkways, and many other interior surfaces requiring additional protection. Kemiko® Easy Shine™ is not intended to be applied over Kemiko® Buff-On Wax II or Kemiko® Repels™. Kemiko® Easy Shine™ is intended for interior use only.

### Physical Characteristics

<b>Kit Size</b>	1 gallon and 5 gallon kits
<b>Colors Available</b>	Clear High Gloss and Satin finish available
<b>Volume Solids</b>	20% volume solids
<b>VOC Contents</b>	<250 g/L (theoretical)
<b>Specific Gravity</b>	1.03 (theoretical)
<b>Coverage Per Kit</b>	1gal: 400ft <sup>2</sup> - 800ft <sup>2</sup> (37.2m <sup>2</sup> - 74.3m <sup>2</sup> ) at recommended wet film thickness 5gal: 2000ft <sup>2</sup> - 4000ft <sup>2</sup> (186m <sup>2</sup> - 371.5m <sup>2</sup> ) at recommended wet film thickness <b>Note:</b> Coverage rates will vary depending on surface texture and porosity Suggested coverage is for non-diluted material. Dilutions will increase coverage
<b>Dry/Recoat Time</b>	Dry to Touch: 20-35 minutes Light Foot Traffic: 1-2 hours Heavy Traffic: 20-24 hours Full Chemical & Physical Resistance Cure: 3-5 days Recoat Window: Within 24 hours after product reaches Dry to Touch state <b>Note:</b> Product tested at 70°F and 30% RH. Dry and recoat times will depend on temperature, humidity and other conditions relative to the environment.
<b>Odor</b>	Low odor
<b>Primers</b>	No primer required
<b>Thinning</b>	Do not thin product
<b>Clean Up</b>	Clean tools with warm water and mild soap
<b>Shelf Life</b>	12 months from date of manufacture



## Concrete Coatings & Floor systems

## TECHNICAL BULLETIN Kemiko® Easy Shine Acrylic Mop On Wax (48 series)

### Packaging Description

#### Weight per Kit:

1Gal: 8.57lbs (3.89kg)

5Gal: 42.85lbs (19.44kg)

#### Kemiko® Easy Shine contains:

1Gal (3.78L) of product in a premeasured 1 gallon (3.78L) container

### Environmental Conditions

Apply between 50°F – 85°F (10°C – 29°C) and 5°F (3°C) above dew point. Avoid using in direct sunlight. Do not apply on rainy or foggy days.

### Storage Conditions

Store between 50°F – 100°F (10°C – 37.8°C). Keep in a cool, well-ventilated area, away from direct sunlight and heat. Store in a segregated and safe area, avoiding all possible sources of ignition.

### Safety

Care should be taken when using this product. During application, use proper protective equipment including, but not limited to; protective eye wear, proper respirator, and protective gloves. Ensure work spaces are well ventilated. Refer to the Application Bulletin for application information. Refer to product label and SDS carefully for more detailed safety information prior to use or handling.

### Disclaimer

Information provided in this technical bulletin is based on laboratory testing and is used as a guideline only. Customer should test the material for their specific application and under their application conditions before using the product on a project.

### Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product that is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss or damage resulting from use of this product.



Contact us for any additional application information.

**EPMAR Corporation - A Quaker Houghton Company**

9930 Painter Ave, Whittier, CA 90605-3254

P: 562.946.8781 F: 562.944.9958

epmar.com | kemiko.com

Rev09.2021